

Claims

1. Cancelled
2. Cancelled
3. Cancelled
4. Cancelled
5. (new) A foaming composition comprising a fluororesin and an electrical insulating whisker, wherein the electrical insulating whisker is at least one selected from aluminum borate, magnesium borate and potassium titanate, and the whisker is from 0.1 μm to 1 μm in a diameter and further the whisker in the foaming composition is contained in an amount of from 0.1 to 1 % by weight.
6. (new) A foaming composition according to claim 5 wherein it is mixed with a foaming agent to create a synthetic resin foam.
7. (new) A foaming composition according to Claim 5 wherein the composition is arranged around a central conductor creating a coaxial insulated cable.